

# Supreme SH 03

## High Impact Polystyrene

### Technical Datasheet



#### CHARACTERISTIC

- High Flow
- Excellent Toughness
- Excellent mold release behaviour

#### PROCESSING

- Molding

#### APPLICATIONS

- Gas assisted injection moulding of TV cabinets
- Suitable for thin walled parts, AC grills, toys, computer accessories, refrigerator components
- Base material for compounding
- Suitable for shoe heel compound.

• **Material status:** Commercially active

• **Agency ratings:** FDA 21 CFR177:1640, UL file No. E185934, RoHS compliant.

Property	ASTM Method	Test Condition	Value	Unit
<b>Rheological</b>				
Melt Flow Index	D1238	200°C/5Kg	8.5	gm/10 min
<b>Thermal</b>				
Vicat Softening Point	D1525	120°C/hr, 1 Kg	98	°C
Heat Deflection temperature	D648	1.86 Mpa	76	°C
<b>Mechanical</b>				
Tensile Strength	D638	50 mm/min	23	Mpa
Elongation	D638	50 mm/min	50	%
Flexural Strength	D790	3.2 mm	36	Mpa
Flexural Modulus	D790	3.2 mm	2200	Mpa
Izod Impact (Notched)	D256	3.2 mm	100	J/m
<b>Flammability</b>				
Glow wire temperature	IEC 695-2-1	-	-	°C
Flammability	UL 94	@1.6mm	HB	-
<b>General</b>				
Specific Gravity	D792	-	1.03	-
<b>Processing Conditions</b>				
Maximum Melt Temperature	-	-	180-260	°C
Pre-drying Temperature	-	2hr	50-80	°C
Mold Temperature	-	-	40-60	°C

Data presented in this catalogue are typical values of properties and are intended to serve as guide only. SPL reserves the right to review the content of this catalogue & revise.



**Contact Details:** Solitaire corporate park, bldg no. 5/11,  
Chakala, Andheri (E), Mumbai – 400 093, Tel: +91-22-6709 1900,  
Fax: +91-22-6709 1924/25, Customer Services: [css@spl.co.in](mailto:css@spl.co.in),  
Export marketing: [export@spl.co.in](mailto:export@spl.co.in), Domestic marketing:  
[marketing@spl.co.in](mailto:marketing@spl.co.in), Website: [www.supremepetrochem.com](http://www.supremepetrochem.com)

# Supreme SH 03

## High Impact Polystyrene

### Technical Datasheet



---

#### Test Method & Standard Properties

Data presented in this catalogue are typical values of properties for natural material and intended to serve as a guide only. All tests are carried out as per ASTM D standard unless otherwise stated. Testing of all mechanical properties is done with an injection molded specimen of 3.2 mm. In actual applications, properties can be affected to a considerable extent by the mould / die design, the processing conditions and the colour.

#### Environmental

Supreme polystyrene resins can be recycled, incinerated or disposed off in landfill without detriment to the environment. Adequate ventilation should be provided during processing. Where recycling of Supreme Polystyrene is not possible, disposal to landfill or incineration in accordance with all applicable government laws and regulations is recommended. Material Safety Data Sheets (MSDS) for Supreme Polystyrene resins are available from Supreme Petrochem Ltd. MSDS are provided to help customers in their own handling, safety and disposal needs and those that may be required for applicable health and safety regulations e.g. OHSAS 18001 and ISO14000. Supreme flame retardant polystyrene grades contains additives which may release hazardous or toxic vapors through lengthy or excessive exposure to high heat. Kindly, refer to recommended processing temperatures and use suitable personal protective equipments.

#### Handling Precautions

While the handling of Supreme polystyrene pellets generally does not present unusual problems, a dust can be formed under some circumstances. If workers are exposed to this dust, they should be protected from dust inhalation by use of approved dust respirators. Contact with the skin and eyes should be prevented by use of protective equipment and/or clothing. SPL recommends storing of polystyrene in cool & dry place in a shade away from sunlight and heat. The packing used is not UV stabilised and hence should not be exposed to sunlight.

#### Exclusion of Liability

The information contained herein is provided for general reference purposes only. By providing the information contained herein, Supreme Petrochem Ltd makes no guarantee or warranty, and does not assume any liability with respect to the accuracy or completeness of such information or the product results in any specific instance and hereby expressly disclaims any implied warranties of merchantability or fitness for a particular purpose or any other warranties or representations whatsoever, expressed or implied. Nothing contained herein shall be construed as a licence to use the products of Supreme Petrochem Ltd in any manner that would infringe any patent.



**Contact Details:** Solitaire corporate park, bldg no. 5/11,  
Chakala, Andheri (E), Mumbai – 400 093, Tel: +91-22-6709 1900,  
Fax: +91-22-6709 1924/25, Customer Service: [css@spl.co.in](mailto:css@spl.co.in),  
Export marketing: [export@spl.co.in](mailto:export@spl.co.in), Domestic marketing:  
[marketing@spl.co.in](mailto:marketing@spl.co.in), Website: [www.supremepetrochem.com](http://www.supremepetrochem.com)